



Report No. A2200406476101

Page 1 of 5

Company Name	LA BUENA SEMILLA LTD.
Show on Report	LA DUENA SEIVILLA LID.
Address	NO. 5, 17/F, BONHAM TRADE CENTER, STRAND 50, 50 BONHAM STRAND,
	SHEUNG WAN, HONG KONG

The following sample(s) and sample information was/were submitted and identified by/on the behalf of		
the client		
Sample Name	Mask Earloop	
Sample Color	White	
Style No.	5mm flat, 3mm round	
Supplier code	LBS	
Brand	LBS	
Sample Source	Client deliver	
Sample Status	In good status	
Sample Received Date	Nov. 17, 2020	
Testing Period	Nov. 17, 2020 to Nov. 19, 2020	

Test Conducted:

As requested by the applicant, for details refer to next page(s)



chen fair

Chen kaimin Technical Manager No. S448709053 No.1351, Wanfang Road, Minhang District, Shanghai, China



Report No. A2200406476101

Page 2 of 5

Summary of Test Result(s)			
Test Item(s)	Test Standard	Test Result/Conclusion	
	FZ/T 01057.1-2007		
	FZ/T 01057.2-2007		
Fiber Analysis	FZ/T 01057.3-2007	See page 3	
	FZ/T 01057.4-2007		
	FZ/T 01095-2002 Method B		
The Elastic Recovery and the			
Plastic Deformation Rate at the	FZ/T 60021-2010	PASS	
Specified Extension			
Elongation rate	FZ/T 60021-2010	PASS	
Elongation at Break	FZ/T 60021-2010	PASS	
Formaldehyde	GB/T 2912.1-2009	PASS	

	Test Request	Applicant's Requirement	
		GB/T 32610-2016	
	********For Further Details, Please Refer to the Following Page(s) ************************************		





Report No. A2200406476101

Page 3 of 5

Tests Conducted (As Requested by the Client)

1 <u>Fiber Analysis(FZ/T 01057.1-2007,FZ/T 01057.2-2007,FZ/T 01057.3-2007,FZ/T 01057.4-2007,FZ/T 01095-2002 Method B)</u>

Tested Item(s)	Test Result	Applicant's Requirement
	002	
Fibre Composition	85.9% Polyamide 14.1% Elastane	

2 Elongation rate(FZ/T 60021-2010)

Elongation rate: 1:3

Tested Item(s)	Test Result		Amiliaant's Dequinement
Tested Item(s)	001	002	Applicant's Requirement
Elongation rate		No broken when the elongation rate reached.	No Broken

3 The Elastic Recovery and the Plastic Deformation Rate at the Specified Extension(FZ/T 60021-2010)

Tested Item(s)	Test Result	Applicant's Dequirement
	002	Applicant's Requirement
Elastic Recovery	84.8%	≥75%

4 <u>Elongation at Break(FZ/T 60021-2010)</u>

Tested Item(s)	Test Result	Amiliaant's Dequinement
Tested Item(s)	002	Applicant's Requirement
Elongation at Break	160N	≥20N

5 Formaldehyde (GB/T 2912.1-2009)

Tested Item(s)	Test Result (mg/kg)	MDL (mg/kg)	Standard Requirement
	002	MDL (IIIg/Kg)	(mg/kg)
Formaldehyde	N.D.	20	≤20

Remark: -MDL = Method Detection Limit -N.D. = Not Detected (<MDL) -mg/kg = ppm = parts per million 用: iervi




Report No. A2200406476101

Tested Sample/Part Description

- 001 White mask earloop(3mm)
- 002 White mask earloop(5mm)

Photo(s) of the sample(s)





002

Page 4 of 5





Report No. A2200406476101

Statement:

1. This report is considered invalidated without approval signature, special stamp;

2.Company name and address show on report, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which CTI hasn't verified;

3. The result(s) shown in this report refer(s) only to the sample(s) tested;

4. Without written approval of CTI, this report can't be reproduced except in full;

5.Except for the requirement of the client, the test results and the conformity assessment in this report do not take the uncertainty into account.

*** End of Report ***

オ国シッシ

Page 5 of 5